

TECHNICAL DATA SHEET

Dy-Mark (Aust) Pty Ltd

PO Box 1556 Toowong 4066

Phone: 1300 396 275 Fax: 1300 360 440

www.dymark.com.au



Dy-Mark ZINC GUARD™ ETCH PRIMER



Dy-Mark Zinc Guard™ Etch Primer has been designed to provide superior adhesion to metals that are difficult to bond to. **Etch Primer** provides high performance corrosion protection and is a suitable base for a range of top coats. A fast dry product, **Etch Primer** is suitable for use on; gates, fences, railings, pipes and gutters. **Etch Primer** dries to a matt grey finish.

DIRECTIONS FOR USE

Suitable Surfaces:

Aluminium, galvanised iron, new steel, ZINCALUME®, copper and brass.

Ideal Application Temperature:

Between 10°C and 40°C. Avoid use in windy conditions.

Preparation:

Etch Primer should not be applied to existing painted surfaces. Surface should be clean, dry and free from contaminants such as; rust, oil, grease, dirt and salt. Thoroughly sand new metal surfaces to ensure maximum adhesion and wipe down thoroughly with **Dy-Mark Acetone**. For aged or lightly rusted surfaces remove loose rust with a wire brush, scraper or mechanical sander and wipe down thoroughly with **Dy-Mark Acetone**.

Application:

Before spraying, cover surrounding areas to protect from overspray. **Shake can** for at least 45 seconds **AFTER** the mixing ball begins to rattle. Shake can occasionally during use. Hold can upright approximately 20-25cm from the surface. Spray with a smooth sweeping motion. To prevent paint from sagging, apply several light mist coats rather than one heavy coat. **Adjust nozzle** to achieve desired spray pattern. Use horizontal setting to spray up and down and the vertical setting to spray across.

Coverage:

Approximately 2m² per can (depending on the surface and amount of overspray).

Drying Time:

Touch dry in 10 minutes (25°C). Recoat after 2 hours. Drying will be slower in cold and humid conditions, in the absence of ventilation or where heavy film build is applied.

After Spraying:

Prevent blocking by holding the can upside down and spraying until only clear gas escapes. Also **wipe spray tip** of nozzle clean. **Clean up** wet paint with, **Dy-Mark Acetone** or **General Purpose Thinner**.

TECHNICAL DATA SHEET

Dy-Mark (Aust) Pty Ltd

PO Box 1556 Toowong 4066

Phone: 1300 396 275 Fax: 1300 360 440

www.dymark.com.au



TECHNICAL DATA

Size:	325g Aerosol
Colour:	Grey
Finish:	Matt
Consistency:	Liquid
Propellant:	Dimethyl ether

STORAGE

Store locked up. Protect from sunlight. Do not expose to temperatures exceeding 50°C/122°F. Store in well ventilated place.

DISPOSAL

Dispose of contents/container according to regional regulations.

FIRST AID / SAFETY INFORMATION

Please refer to Safety Data Sheet before use. Safety data sheets are available from our website www.dymark.com.au or from the following QR code:



Call a POISON CENTRE: Australia 13 11 26, New Zealand 0800 764 766 or doctor/physician if you feel unwell.

Intentional misuse by deliberately inhaling contents can be harmful or fatal.

KEEP OUT OF REACH OF CHILDREN.

TECHNICAL DATA SHEET

Dy-Mark (Aust) Pty Ltd

PO Box 1556 Toowong 4066

Phone: 1300 396 275 Fax: 1300 360 440

www.dymark.com.au



DISCLAIMER

The information provided within this Technical Data Sheet is intended as a guide only. The performance of this product will depend on many factors outside the control of Dy-Mark; including surface preparation, surface-specific conditions, surface types, correct application and environmental conditions.

Dy-Mark recommends customers undertake their own risk assessment prior to use, to determine the suitability of the product for the particular use intended.

It is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs on the specific surface.

For further information please contact the Dy-Mark Sales and Customer Support Centre on 1300 396 275.